

ASTM 5272 TEST RESULTS

# ECOgrade-CW Photodegradation Test

## Q-LABS - ASTM D5272 Standard



Q-Lab Weathering Research Service  
1005 S.W. 18 Avenue  
P. O. Box 349490  
Homestead, FL 33034

**TEST CERTIFICATE**  
Natural Weathering

Test Program Number:	GGM-1-TP-1
Company:	GXT Green
Address:	505 Middlesex Turnpike - Suite 11 Billerica, MA 01821
Attention:	Mr. Michael Vanh
Your Reference:	
No. Of Specimens:	1
Specimen Identification:	See following page.
Test Method:	Per Client Instructions
Deviations:	None
Exposure Date:	June 30, 2011
Completion Date:	February 25, 2012
Exposure Duration:	7 Months 26 Days
Exposure Type:	Direct Weathering- Florida 5° South Backed
Radiation Exposure:	Total = 3,754.86 MJ/m2 TUVr = 206.81 MJ/m2
By:	 Rosie Rosario Test Set Up Supervisor
Approved By:	 Ian Collishaw Site Manager

Specimen has totally degraded.

